



Phone: (402) 999-0827 Email: info@eleavationpkg.com www.elevationpkg.com

TEST REPORT

FILM: EP255

MATERIAL: PET/AP/LLDPE

SIZE: 0.072x240 mm

Test Item (s)	UNIT	VALUE	TEST METHOD
TOTAL THICKNESS	micro	72	---
PET	micro	12	---
PE	micro	30	---
EVA/SEALANT LAYER	micro	30	---
O ₂ PERMEABILITY	cc/m ² /24hrs(25°C, DRY)	137	ASTM D3985
H ₂ O PERMEABILITY	g/m ² /24hrs(23°C, 50%RH)	3.786	ASTM E96 METHOO B
SEALING TEMPERATURE	°C	---	---
THERMICAL TREATMENTS	80°C-20min	---	---
TENSILE STRENGTH	MD	kg/mm ²	JIS K 6732
	TD		
			2.965